UL 1333

-60°C to +150°C, 300V



Construction
Conductor: Tinned Copper or Bare Copper
Insulation: Extruded · FEP

Thermal Characteristics
Operating Temperature: -60°C to +150°C

Electrical Characteristics
Operating Voltage: 300V

Application
Internal wiring: Internal wiring of appliances and electronic equipment.
High-temperature equipment: High-temperature lead wiring for industrial controls, lighting fixtures, and heating appliances.

General Characteristics
Thermal & Soldering Stability: Superior high-temperature stability with zero melt-back or shrinkage during soldering.
Chemical & Solvent Inertness: Exceptional resistance to oils, fuels, acids, alkalis, and aggressive industrial solvents.
Low Dielectric Loss: Low dielectric constant and high dielectric strength for reliable signal and power integrity.

Standards & Approvals
UL 758: UL 758 Appliance Wiring Material, Style 1333.
CSA C22.2 No. 210: cUL Appliance Wiring Material, Style 1333.

Fire Performance
Fire Retardant: VW-1 / FT1 / FT2

CASMO Part No.	Conductor				Insulation		Nom. O.D. (mm)	Max. DCR @20°C (Ω/km)	Nom. Cable Weight (kg/km)
	Conductor Size (AWG)	No. Of Strands	Nom. Strand Dia. (mm)	Nom. Conductor Dia. (mm)	Nom. Ins. Thickness (mm)	Min. Ins. Thickness (mm)			
1210830/7-TS-XX	30	7	0.1	0.3	0.33	0.3	0.96	381	1.91
1210828/7-TS-XX	28	7	0.127	0.38	0.33	0.3	1.04	239	2.42
1210826/7-TS-XX	26	7	0.16	0.48	0.33	0.3	1.15	150	3.45
1210824/11-TS-XX	24	11	0.16	0.61	0.33	0.3	1.3	94.2	4.65
1210824/19-TS-XX	24	19	0.127	0.64	0.33	0.3	1.3	94.2	4.85
1210822/7-TS-XX	22	7	0.254	0.76	0.33	0.3	1.42	59.4	6.37
1210822/17-TS-XX	22	17	0.16	0.76	0.33	0.3	1.42	59.4	6.37
1210820/19-TS-XX	20	19	0.2	1	0.33	0.3	1.66	36.7	9.62
1210820/26-TS-XX	20	26	0.16	0.94	0.33	0.3	1.66	36.7	9
1210820/41-TS-XX	20	41	0.127	0.94	0.33	0.3	1.66	36.7	9
1210818/19-TS-XX	18	19	0.254	1.27	0.33	0.3	1.93	23.2	14.25
1210818/41-TS-XX	18	41	0.16	1.18	0.33	0.3	1.93	23.2	13.09
1210816/26-TS-XX	16	26	0.254	1.49	0.33	0.3	2.16	14.6	19.63
1210816/65-TS-XX	16	65	0.16	1.5	0.33	0.3	2.16	14.6	19.79
1210814/41-TS-XX	14	41	0.254	1.88	0.33	0.3	2.6	8.96	30.12
1210814/104-TS-XX	14	104	0.16	1.89	0.33	0.3	2.6	8.96	30.32
1210812/65-TS-XX	12	65	0.254	2.36	0.33	0.3	3.32	5.64	48.1
1210812/168-TS-XX	12	168	0.16	2.37	0.33	0.3	3.32	5.64	48.35

Please confirm application-specific requirements with CASMO before ordering. Specifications are subject to change; please ensure you are using the latest revision.

© CASMO CABLE LLC. All rights reserved.

UL 1333

-60°C to +150°C, 300V



CASMO Part No.	Conductor				Insulation		Nom. O.D. (mm)	Max. DCR @20°C (Ω/km)	Nom. Cable Weight (kg/km)
	Conductor Size (AWG)	No. Of Strands	Nom. Strand Dia. (mm)	Nom. Conductor Dia. (mm)	Nom. Ins. Thickness (mm)	Min. Ins. Thickness (mm)			
1210810/105-TS-XX	10	105	0.254	2.98	0.33	0.3	3.64	3.54	69.29
1210810/259-TS-XX	10	259	0.16	2.97	0.33	0.3	3.64	3.54	69.07

Table Notes

* Part No. code: XX = colour code — BK Black, WH White, RD Red, GN Green, BN Brown, BL Blue, OR Orange, YW Yellow, VT Violet, GY Grey, PK Pink, TN Tan, CL Clear.

† "-TS-" = tinned copper conductor, "-AS-" = bare copper conductor; TS and AS may be substituted for each other.

Please confirm application-specific requirements with CASMO before ordering. Specifications are subject to change; please ensure you are using the latest revision.

© CASMO CABLE LLC. All rights reserved.