

CASFLON™ SAE

AS22759 / 9 / 10 / 11 / 12

-65°C to +200°C or 260°C , 1000V or 600V



Construction

Type: electrical wire

Core: silver-plated copper or nickel plated copper

Insulation: extruded PTFE

Production

Range width: AWG 28 to 8

Options: contact us for more options

Application

Aviation: Electrical lightweight cables used in electronic equipment for aircraft, missile systems or aeronautical test benches

General characteristics

Weather conditions: excellent resistance to UV

Chemical behaviors: excellent resistance to aggressive chemical environments

Humidity: excellent resistance to humidity

Mechanical behaviors: excellent mechanical strength

Thermal characteristics

Operating temperature: SPC: -65°C to +200°C

NPC: -65°C to +260°C

Electrical characteristics

Operating Voltage: AS22759 /9 /10 : 1000V

AS22759 /11 /12 : 600V

Approvals – Standards

NEMA standard: MIL-W-22759/ 9 / 10 / 11 / 12

AS22759 / 9 , ex. MIL-W-22759 / 9 1000V

AWG/Stranding	Insulation Thickness		O.D.		Weight	
	(inch)	(mm)	(inch)	(mm)	(lbs/mft)	(kg/km)
28 7/36	0.014	0.356	0.043	1.09	2	2.98
26 19/38	0.015	0.381	0.048	1.22	3	4.46
24 19/36	0.015	0.381	0.053	1.35	4	5.95
22 19/34	0.015	0.381	0.06	1.52	5	7.44
20 19/32	0.015	0.381	0.068	1.73	7	10.42
18 19/30	0.015	0.381	0.078	1.98	9	13.39
16 19/29	0.015	0.381	0.085	2.16	11	16.37
14 19/27	0.016	0.406	0.1	2.54	17	25.30
12 19/25	0.017	0.432	0.12	3.05	24	35.71

COPYRIGHT

This document is protected under copyright law and is the property of Casmo Cable. Data contained herein is confidential to Casmo Cable and this document and/or any part of the data contained herein may not be copied, duplicated, or released for the manufacturing or sale of equipment outside of Casmo Cable or any affiliates without the prior written authorization of Casmo Cable

CAUTION

The information included in this catalog is intended as a guideline only. For applications that require tight tolerances, please contact Casmo Cable for dimensional verification, information herein is believed to be accurate as of the publication date; however, if an error exists it is unintentional and Casmo Cable is not responsible for any claim traceable to such error.



www.casmocable.com

CASFLON™ SAE

AS22759 / 9 / 10 / 11 / 12

-65°C to +200°C or 260°C, 1000V or 600V



AS22759 / 10 , ex. MIL-W-22759 / 10 1000V

AWG/Stranding	Insulation Thickness		O.D.		Weight	
	(inch)	(mm)	(inch)	(mm)	(lbs/mft)	(kg/km)
28 7/36	0.014	0.356	0.043	1.09	2	2.98
26 19/38	0.014	0.356	0.048	1.22	3	4.46
24 19/36	0.014	0.356	0.053	1.35	4	5.95
22 19/34	0.015	0.381	0.06	1.52	5	7.44
20 19/32	0.015	0.381	0.068	1.73	7	10.42
18 19/30	0.015	0.381	0.078	1.98	9	13.39
16 19/29	0.015	0.381	0.085	2.16	11	16.37
14 19/27	0.016	0.406	0.1	2.54	17	25.30
12 19/25	0.017	0.432	0.12	3.05	24	35.71

AS22759 / 11 , ex. MIL-W-22759 / 11 600V

CASMO P.N.	CASMO P.N.		CASMO P.N.		CASMO P.N.	
	CASMO P.N.	CASMO P.N.	CASMO P.N.	CASMO P.N.	CASMO P.N.	CASMO P.N.
28 7/36	0.009	0.229	0.033	0.84	2	2.98
26 19/38	0.01	0.254	0.038	0.97	2	2.98
24 19/36	0.01	0.254	0.043	1.09	3	4.46
22 19/34	0.009	0.229	0.049	1.24	4	5.95
20 19/32	0.01	0.254	0.058	1.47	6	8.93
18 19/30	0.01	0.254	0.068	1.73	8	11.90
16 19/29	0.01	0.254	0.075	1.91	10	14.88
14 19/27	0.011	0.279	0.09	2.29	15	22.32
12 19/25	0.013	0.330	0.111	2.82	23	34.23
10 37/26	0.015	0.381	0.139	3.53	35	52.08
8 133/29	0.019	0.483	0.204	5.18	66	98.21

COPYRIGHT

This document is protected under copyright law and is the property of Casmo Cable. Data contained herein is confidential to Casmo Cable and this document and/or any part of the data contained herein may not be copied, duplicated, or released for the manufacturing or sale of equipment outside of Casmo Cable or any affiliates without the prior written authorization of Casmo Cable.

CAUTION

The information included in this catalog is intended as a guideline only. For applications that require tight tolerances, please contact Casmo Cable for dimensional verification, information herein is believed to be accurate as of the publication date; however, if an error exists it is unintentional and Casmo Cable is not responsible for any claim traceable to such error.



CASFLON™ SAE

AS22759 / 9 / 10 / 11 / 12

-65°C to +200°C or 260°C , 1000V or 600V



AS22759 / 12 , ex. MIL-W-22759 / 12 600V

AWG/Stranding	Insulation Thickness		O.D.		Weight	
	(inch)	(mm)	(inch)	(mm)	(lbs/mft)	(kg/km)
28 7/36	0.009	0.229	0.033	0.84	2	2.98
26 19/38	0.01	0.254	0.038	0.97	2	2.98
24 19/36	0.01	0.254	0.043	1.09	3	4.46
22 19/34	0.009	0.229	0.049	1.24	4	5.95
20 19/32	0.01	0.254	0.058	1.47	6	8.93
18 19/30	0.01	0.254	0.068	1.73	8	11.90
16 19/29	0.01	0.254	0.075	1.91	10	14.88
14 19/27	0.011	0.279	0.09	2.29	15	22.32
12 19/25	0.013	0.330	0.111	2.82	23	34.23
10 37/26	0.015	0.381	0.139	3.53	35	52.08
8 133/29	0.019	0.483	0.204	5.18	66	98.21

COPYRIGHT

This document is protected under copyright law and is the property of Casmoc Cable. Data contained herein is confidential to Casmoc Cable and this document and/or any part of the data contained herein may not be copied, duplicated, or released for the manufacturing or sale of equipment outside of Casmoc Cable or any affiliates without the prior written authorization of Casmoc Cable.

CAUTION

The information included in this catalog is intended as a guideline only. For applications that require tight tolerances, please contact Casmoc Cable for dimensional verification, information herein is believed to be accurate as of the publication date; however, if an error exists it is unintentional and Casmoc Cable is not responsible for any claim traceable to such error.

